

PUR 840-M

2K Matt Anti-corrosion Polyurethane

PRODUCTS

Pigmented bases	DISOLAC	20
Binder	PUR 840-M	80
Hardener	E9005 standard	4:1
	E9003 slow	4:1
	E9006 fast	4:1
Thinner	SOLV UNIVERSAL 5	0-20%
	SOLV UNIVERSAL 3	0-20%

DESCRIPTION AND PROPERTIES

- Polyurethane monolayer finish.
- Mate – can be mixed with PUR 840G to achieve the desired level of brightness (As shown in the brightness table in Annex A)
- Good chemical resistance.
- Coating with anticorrosive protection.
- Direct adhesion to iron, stainless steel, galvanized, cast iron, electrozinc, aluminium, ABS, PVC, methacrylate and gel coat .
- Reaction to fire CLASS B-s1,d0 (UNE-EN 13501-1:2007+A1:2010).
- The product must be applied in installations that comply with Directive 1999/13/EC.

CHARACTERISTICS OF PUR 840-M

Appearance	Matt	
Gloss	approx. 10% at 60°, 20-25% at 85°	
Specific weight of the Binder	1,1 kg/l at 20°C	
Solid content (binder)	50-54% (weight)	38-43% (volume)
Solid content ready to use	48-55 % (weight)	37-42% (volume)
VOC ready to use 20% dilution	> 500 g/l - 2004/42/EC - IIA(j)(500)	
Dry film thickness	60-70 microns (2 coats)	
Theoretical yield 1 µm per litre of binder	380-430 m ² /l	
Theoretical yield 1 µm per litre of mixing 20% dilution	370-420 m ² /l	
Corrosion category system 840-M (ISO 12944)	C3 high /C4 medium	





SUBSTRATE AND PREPARATION OF THE SURFACE

	CLEANING	SANDING	FINAL CLEANING
Old paints	DA93	P360/400	DA93
Plastic parts	--	--	--
Steel	DA93	P360/400	DA93
Galvanised steel	DA93	P360/400	DA93
Aluminium	DA93	P360/400	DA93
PRIMERS			
Primanyl 5011	DA93	---	---
Primapox 6021	DA93	Optional (P320)	DA93
Primapox 6041	DA93	Optional (P320)	DA93
Primapur 9051	DA93	Optional (P320)	DA93

For other kind of substrates consult the Technical Service (SAT).



APPLICATION

	SMALL SURFACE		LARGE SURFACE	
	Hardener	Thinner	Hardener	Thinner
T(°C)				
18-25	E9005/E9006	SOLV UNIVERSAL 5	E9005	SOLV UNIVERSAL 5
>25	E9005	SOLV UNIVERSAL 5	E9005/E9003	SOLV UNIVERSAL 3

	Mixing ratio Disolac/Binder (in weight)				20/80			
	Mixing ratio Hardener (in volume)				Pigmented		Clear coat	
					4:1		---	
Electrostatic application (in volume)				---				
	Application	% thinner (VOLUMEN)	Viscosity (20°C) Ford Cup 4	Pressure (BAR)	Product pressure (BAR)	Nozzle (mm)	N°Coats x µm dry	Flash off (min)
	Gravity feed spray gun	10-15%	20"-23" F/4 20°C	2-3	---	1,3-1,5	2x25	10' 20°C
	Pot life:	8 hours						

If the application requires the use of an additive, it should be taken into account in the addition of solvent.

DRYING

 TEMPERATURE	 HANDLING	THROUGH DRY
20° C	1h-1h30'	3h-3h30'
60° C	---	30'

The product reaches its maximum performance after 15 days of drying in the air (ambient temperature 18-22°C) or in a shorter time at a higher temperature.

ADDITIONAL ADDITIVES FOR SPECIAL USES

SITUATION	ADDITIVE	DESCRIPTION	EFFECT
Craters	Additive Anticrater Disolac	Film protection from outdoor polluting agents	Anticrater; film protection
Weathering resistance /UV filters	Additive UV	Protection of the coating film against UV layers	Increases the durability of the coating film
Overspray sensitivity /Too fast drying of the film	Flow Additive	Improve the application, for example in the application of large surfaces or in dry conditions	Keeps the film opened for a longer time
Fast drying	E9006	Decreases drying times if needed	Decreases drying times
Slow drying	E9003	Increases drying times if needed	Increases drying times
Degreasing	DIS226 DA93	DIS226 for plastics and surfaces electrostatically chargeable. DA93 for greasy surfaces.	

For use and instructions of the additives consult the technical data sheet of each product.

REMARKS

- Recommended to be used in ventilated spray booth at 20°C.

EQUIPMENT CLEANING

- Use a cleaning thinner before the pot life expired.



SAFETY

- Follow instructions of product label.
- For more information check the Safety Data Sheet.
- Compliant with the National Statutory Regulation for Health and Safety at Work and Waste Disposal.

STORAGE

- Store the product in a ventilated place far from direct exposure to sunlight.
- Keep between +5°C and +30°C.

GUARANTEE

- One year in unopened original packaging



ANNEX A

Gloss chart

PUR 840G	PUR 840M	E9005 (in volume of colour)	GLOSS ([^] 60°)	CATEGORY
100	0	4:1	>90	GLOSSY
75	25	4:1	70-90	SEMI-GLOSSY
50	50	4:1	40-70	SATIN
25	75	4:1	20-40	SATIN
0	100	4:1	<20	MATT

Degree of brightness obtained by the ratio of Pigmented Base / Binder mixture (20/80).

The desired gloss level depends on the applied colour, thickness, substrate and drying temperature.

These products are for professional use only. The Safety Data Sheet should be consulted before use and the precautionary warnings on the product packaging should be observed. Its correct use, according to its purpose and respecting its technical and security data, provided in these documents, is the sole and exclusive responsibility of the user. ROBERLO S.A.U declines any liability due to the incorrect use of any product.

The information included in this documentation is based on our scientific and technical knowledge on the date of its issuance. ROBERLO S.A.U reserves the right to modify and/or discontinue all or part of the information at any time and without prior notice. It is the user's responsibility to verify the update of the information. The latest version of this document replaces all previous versions.

All clauses contained herein apply to any future changes or modifications.

For any additional technical information please consult with our Customer Service or our Technical Department.

