

Technical Information Sheet

Fas-Trac Service

September 20, 2012

Type: HAA Polyester

NUMBER: HFTR02S8

NAME: RAL 1019 HAA

POWDER PROPERTIES

ASTM D5965-96, C	Specific Gravity Theoretical Coverage	1.5 ± 0.05 128 f⊄ /lb/mil
ASTM D3451-92, 13	Mass Loss During Cure	< 1 %
	Recommended Shelf Life:	12 Months @ 75 F

COATING PROPERTIES

ASTM D523-89	Gloss at 60°	75-85
DPC TM 10.219	PCI Powder Smoothness	7
ASTM D3363-92a	Pencil Hardness	2H
ASTM D2794-93	Dir / Rev Impact, Gardner	160 / 160 in/lbs
ASTM D522-93a	Flexibility, Mandrel	1/8 in. dia., no fracture
ASTM B117-97	Salt Spray	1,000 hrs
UL DTOV2 Organic Coating	Steel Enclosures, Elect. Eq.	Recognized

APPLICATION

Electrostatic Spray, Cold Substrate: 0.032 in. CRS Pretreatment: Bonderite 1000®, Parcolene® 60

Cure Schedule:

(Time at substrate temperature) 10 Minutes @ 375F or 15 Minutes @ 350F **Film Thickness:** 2.0-3.0 Mils

Prepared 6/25/2013

This coating has been developed to meet or exceed the requirements of AAMA 2603 on architectural aluminum components.

9800 Genard Rd. Houston, TX 77041-7624 4130 Lyman Dr. Hilliard, OH 43026-1213 1-800-247-3886 1-800-667-9610

fax: 713-939-4027 fax: 614-771-4139

WARRANTY POLICY: Seller certifies that all coatings delivered to Customer in unopened factory filled containers meet all pertinent quality standards presented in its current published literature. Since matters of surface preparation, application procedures, curing procedures and other local factors that affect coating performance are beyond Seller's control, Seller assumes no liability for coating failure other than to supply replacement material for a coating material proven to be defective. Customer will determine suitability of this product for its use and thereby assume all risks and liabilities in connection therewith. Seller will not be liable for any injuries, damages or other losses derived, directly or indirectly, from or as a consequence of Customer's use of the product. SELLER DISCLAIMS ALL OTHER WARRANTIES, EXPRESS OR IMPLIED, RELATING TO ITS PRODUCTS AND THEIR APPLICATION, INCLUDING BUT NOT LIMITED TO WARRANTIES OF MERCHANTABILITY AND FITNESS FOR PARTICULAR PURPOSES.

