Technical Information Sheet



ALESTA AR300*

Number: HFSR02S8

RAL 2001 HAA Name:

Alesta Group Code: AE80002000016

September 20, 2012

Type: HAA Polyester

POWDER PROPERTIES

ASTM D5965-96, C Specific Gravity

Theoretical Coverage

 1.58 ± 0.05 122 ft2/lb/mil

ASTM D3451-92, 13

Mass Loss During Cure

Recommended Shelf Life:

< 1%

12 Months @ 75°F

COATING PROPERTIES

ASTM D523-89 Gloss at 60°

DPC TM 10.219

PCI Powder Smoothness

ASTM D2454-95

Overbake Resistance, Time

Pencil Hardness

ASTM D3363-92a ASTM D2794-93

Dir / Rev Impact, Gardner

ASTM D3359-97

Adhesion, Cross Hatch

ASTM D522-93a

Flexibility, Mandrel

ASTM B117-97

Salt Spray **UL DTOV2 Organic Coating**

1/8 in. dia., no fracture

5B Pass

75-85

100%

1,000 hrs

Steel Enclosures, Elect. Eq.

Recognized

160 / 160 in/lbs

APPLICATION

Electrostatic Spray, Cold Substrate: 0.032 in. CRS

Pretreatment: Bonderite® 1000, Parcolene® 60

CURE SCHEDULE:

(Time at substrate temperature)

10 Minutes @ 375°F or 15 Minutes @ 350°F

FILM THICKNESS: 2.5-3.5 Mils

This coating has been developed to meet or exceed the requirements of AAMA 2603 on architectural aluminum components.

Prepared 6/25/2013

4130 Lyman Dr.

9800 Genard Rd. Houston, TX 77041-7624 Hilliard, OH 43026-1213

1-800-247-3886 1-800-667-9610

fax: 713-939-4027 fax: 614-771-4139

POWDER COATED TOUGH SO FIND

WARRANTY POLICY: Seller certifies that all coatings delivered to Customer in unopened factory filled containers meet all pertinent quality standards presented in its current published literature. Since matters of surface preparation, application procedures, curing procedures and other local factors that affect coating performance are beyond Seller's control, Seller assumes no liability for coating failure other than to supply replacement material for a coating material proven to be defective. Customer will determine suitability of this product for its use and thereby assume all risks and liabilities in connection therewith. Seller will not be liable for any injuries, damages or other losses derived, directly or indirectly, from or as a consequence of Customer's use of the product. SELLER DISCLAIMS ALL OTHER WARRANTIES, EXPRESS OR IMPLIED, RELATING TO ITS PRODUCTS AND THEIR APPLICATION, INCLUDING BUT NOT LIMITED TO WARRANTIES OF MERCHANTABILITY AND FITNESS FOR PARTICULAR PURPOSES.



^{*}This product meets the requirements of AAMA 2603.