# **Technical Information Sheet**



## ALESTA AR300\*

 Number:
 HFPR02S7
 May 30, 2013

 Name:
 RAL 4003 HAA
 Type: HAA Polyester

Alesta Group Code: AE70003000116

#### **POWDER PROPERTIES**

**ASTM D5965-96, C** Specific Gravity  $1.52 \pm 0.05$ 

Theoretical Coverage 127 ft2/lb/mil

**ASTM D3451-92, 13** Mass Loss During Cure < 1%

Recommended Shelf Life: 12 Months @ 75 F

#### **COATING PROPERTIES**

 ASTM D523-89
 Gloss at 60°
 70-80

 DPC TM 10.219
 PCI Powder Smoothness
 7

 ASTM D2454-95
 Overbake Resistance, Time
 100%

 ASTM D3363-92a
 Pencil Hardness
 2H

 ASTM D2794-93
 Dir / Rev Impact, Gardner
 160 / 160 in/lbs

 ASTM D3359-97
 Adhesion, Cross Hatch
 5B Pass

**ASTM D522-93a** Flexibility, Mandrel 1/8 in. dia., no fracture

ASTM B117-97 Salt Spray 1,000 hrs

UL DTOV2 Organic Coating Steel Enclosures, Elect. Eq. Recognized

AAMA2603-05 Organic Coatings on Aluminum Passed

Extrusions

### **APPLICATION**

Electrostatic Spray, Cold Substrate: 0.032 in. CRS

Pretreatment: Bonderite® 1000, Parcolene® 60

**CURE SCHEDULE:** 

(Time at substrate temperature)
10 Minutes @ 375F
or 15 Minutes @ 350F

FILM THICKNESS: 2.0-3.0 Mils

This coating has been developed to meet or exceed the requirements of AAMA 2603 on architectural aluminum components.

Prepared 6/24/2013

9800 Genard Rd. Houston, TX 77041-7624 1-800-247-3886 fax: 713-939-4027 COATED 1-800-667-9610 fax: 614-771-4139 POWDER 1-800-667-9610 fax: 614-771-4139

WARRANTY POLICY: Seller certifies that all coatings delivered to Customer in unopened factory filled containers meet all pertinent quality standards presented in its current published literature. Since matters of surface preparation, application procedures, curing procedures and other local factors that affect coating performance are beyond Seller's control, Seller assumes no liability for coating failure other than to supply replacement material for a coating material proven to be defective. Customer will determine suitability of this product for its use and thereby assume all risks and liabilities in connection therewith. Seller will not be liable for any injuries, damages or other losses derived, directly or indirectly, from or as a consequence of Customer's use of the product. SELLER DISCLAIMS ALL OTHER WARRANTIES, EXPRESS OR IMPLIED, RELATING TO ITS PRODUCTS AND THEIR APPLICATION, INCLUDING BUT NOT LIMITED TO WARRANTIES OF MERCHANTABILITY AND FITNESS FOR PARTICULAR PURPOSES.



<sup>\*</sup>This product meets the requirements of AAMA 2603.