Technical Information Sheet



Number: HFYR03S8

RAL 1023 HAA

Alesta Group Code: AE80001000216

September 20, 2012

Type: HAA Polyester

POWDER PROPERTIES

ASTM D5965-96, C

Name:

Specific Gravity

 1.59 ± 0.05

Theoretical Coverage

121 ft2/lb/mil

ASTM D3451-92, 13

Mass Loss During Cure

< 1%

Recommended Shelf Life:

12 Months @ 75°F

COATING PROPERTIES

ASTM D523-89

Gloss at 60°

75-85

DPC TM 10.219

PCI Powder Smoothness

7

ASTM D2454-95

Overbake Resistance, Time

100%

ASTM D3363-92a

Pencil Hardness

2H 160 / 160 in/lbs

ASTM D2794-93 ASTM D3359-97 Dir / Rev Impact, Gardner Adhesion, Cross Hatch

5B Pass

ASTM D522-93a

1/8 in. dia., no fracture

ASTM B117-97

Flexibility, Mandrel

Salt Spray

1.000 hrs

UL DTOV2 Organic Coating

Steel Enclosures, Elect. Eq.

Recognized

APPLICATION

Electrostatic Spray, Cold

Substrate: 0.032 in. CRS

Pretreatment: Bonderite® 1000, Parcolene® 60

CURE SCHEDULE:

(Time at substrate temperature)

10 Minutes @ 375°F

or 15 Minutes @ 350°F

FILM THICKNESS: 2.5-3.5 Mils

This coating has been developed to meet or exceed the requirements of AAMA 2603 on architectural aluminum components.

Prepared 6/25/2013

4130 Lyman Dr.

9800 Genard Rd. Houston, TX 77041-7624 Hilliard, OH 43026-1213

1-800-247-3886 1-800-667-9610

fax: 713-939-4027 fax: 614-771-4139

WARRANTY POLICY: Seller certifies that all coatings delivered to Customer in unopened factory filled containers meet all pertinent quality standards presented in its current published literature. Since matters of surface preparation, application procedures, curing procedures and other local factors that affect coating performance are beyond Seller's control, Seller assumes no liability for coating failure other than to supply replacement material for a coating material proven to be defective. Customer will determine suitability of this product for its use and thereby assume all risks and liabilities in connection therewith. Seller will not be liable for any injuries, damages or other losses derived, directly or indirectly, from or as a consequence of Customer's use of the product. SELLER DISCLAIMS ALL OTHER WARRANTIES, EXPRESS OR IMPLIED, RELATING TO ITS PRODUCTS AND THEIR APPLICATION, INCLUDING BUT NOT LIMITED TO WARRANTIES OF MERCHANTABILITY AND FITNESS FOR PARTICULAR PURPOSES.

