

## **Technical Information Sheet**

### ALESTA AR300\*

### Number: *HFGR*27S7

Name: RAL 6007 HAA

Alesta Group Code: AE70006000516

# <u>August 19, 2013</u>

Type: HAA Polyester

### **POWDER PROPERTIES**

ASTM D5965-96, C	Specific Gravity Theoretical Coverage	1.53 ± 0.05 126 ft2/lb/mil
ASTM D3451-92, 13	Mass Loss During Cure Recommended Shelf Life:	< 1% 12 Months @ 75 F

### COATING PROPERTIES

Gloss at 60°	70-80
PCI Powder Smoothness	7
Overbake Resistance, Time	100%
Pencil Hardness	2H
Dir / Rev Impact, Gardner	160 / 160 in/lbs
Adhesion, Cross Hatch	5B Pass
Flexibility, Mandrel	1/8 in. dia., no fracture
Salt Spray	1,000 hrs
Steel Enclosures, Elect. Eq.	Recognized
Organic Coatings on Aluminum Extrusions	Passed
	PCI Powder Smoothness Overbake Resistance, Time Pencil Hardness Dir / Rev Impact, Gardner Adhesion, Cross Hatch Flexibility, Mandrel Salt Spray Steel Enclosures, Elect. Eq. Organic Coatings on Aluminum

### **APPLICATION**

Electrostatic Spray, Cold Substrate: 0.032 in. CRS Pretreatment: Bonderite® 1000, Parcolene® 60

\*This product meets the requirements of AAMA 2603.

This coating has been developed to meet or exceed the requirements of AAMA 2603 on architectural aluminum components.

9800 Genard Rd. Houston, TX 77041-7624 4130 Lyman Dr. Hilliard, OH 43026-1213 1-800-247-3886 1-800-667-9610

-3886 fax: 713-939-4027 -9610 fax: 614-771-4139

Prepared 8/22/2013

**CURE SCHEDULE:** 

10 Minutes @ 375F

or 15 Minutes @ 350F

(Time at substrate temperature)

FILM THICKNESS: 2.0-3.0 Mils

TOUGH ISO 2001

WARRANTY POLICY: Seller certifies that all coatings delivered to Customer in unopened factory filled containers meet all pertinent quality standards presented in its current published literature. Since matters of surface preparation, application procedures, curing procedures and other local factors that affect coating performance are beyond Seller's control, Seller assumes no liability for coating failure other than to supply replacement material for a coating material proven to be defective. Customer will determine suitability of this product for its use and thereby assume all risks and liabilities in connection therewith. Seller will not be liable for any injuries, damages or other losses derived, directly or indirectly, from or as a consequence of Customer's use of the product. SELLER DISCLAIMS ALL OTHER WARRANTIES, EXPRESS OR IMPLIED, RELATING TO ITS PRODUCTS AND THEIR APPLICATION, INCLUDING BUT NOT LIMITED TO WARRANTIES OF MERCHANTABILITY AND FITNESS FOR PARTICULAR PURPOSES.

